

Herkules 4000 Film Tape with Acrylic Adhesive

Created: Updated: 2008-03-20 2018-01-04

GENERAL INFORMATION

Herkules 4000 is a double sided tape with a PET-film carrier coated with a pure acrylic adhesive. Has a good initial tack, holding power, weatherability, and adheres well on most surfaces and materials.

- 0,22mm thick
- Acrylic adhesive
- Temperature resistant up to 130°C
- High initial tack

Herkules 4000 can be die-cut for custom made parts and is available in all dimensions but standard widths are:

- 9mm x 50m
- 12mm x 50m
- 15mm x 50m
- 19mm x 50m
- 25mm x 50m

CONSTRUCTION



APPLICATIONS

Herkules 4000 adheres well on many different types of surfaces and materials and has a good initial adhesion, which makes it suitable for applications in various industries and applications requiring permanent and strong bonding.

- Adhering and fixing molding and window decorations
- Self-adhesive mounting of decorative and packaging materials
- Other permanent bonding applications
- Bonding of foils, fabrics, paper and plastic materials

USER GUIDELINES

To obtain optimal adhesion the surfaces must be clean and dry. Most frequent cleaning solvent is isopropyl/water (50:50 mixture) alcohol. Use safety instructions before using cleaners. Sometimes depending on surface a primer can be used to obtain a higher bonding force. Ideal temperature for tape application is between 21°C and 38°C.



PRODUCT DATA

Physical Data:

Adhesive:	Acrylic
Carrier:	PET-film
Thickness:	0,22mm
Liner:	Red film or yellow glassine
Colour:	Transparent
Shelf life*:	2 years
Storage:	Good storage conditions are in room
	temperature. Not recommended for direct
	exposure to sunlight or ultraviolet light.

* From date of dispatch by ATC Tape Converting AB

Performance Data:

Holding power: A/B side (PSTC-7)	24 hrs, 1kg/25mm ²
Holding Power for Temp. resistance 60°C: (PSTC-7)	24h 0,5kg/25mm ²
Adhesion: A/B side (PSTC-1)	24,40-32,21 N/25mm
Initial tack: A/B side (PSTC-6#14 ball)	5 cm
Peel strength:	>2 500 g/25mm
Solvent resistance:	Good
Heat resistance:	Up to +130°C

CONTACT INFORMATION

ATC Adhesive Tape Converting AB	
Veddestavägen 17, Box 575	
175 26 Järfälla, SWEDEN	

Telephone: +46 (0)8-564 708 80 Fax: +46 (0)8-564 708 89

E-mail: Web: info@atc.se

www.atc.se



Intertek Intertek

All values above are average values and are not to be specific. To be sure about finished result we recommend that you do testing and use the product to determinate the function of the tape for your application. ATC Adhesive Tape Converting AB does NOT take any responsibility or liability direct or consequential for any loss or damage caused by using our product.