# Herkules 7010
## Cloth Tape with Acrylic Adhesive

Created:     2010-12-28
Updated:     2018-01-04

## GENERAL INFORMATION

Herkules 7010 is a double sided tape with a rayon carrier coated with a soft acrylic adhesive. Easy to tear by hand and leaves no residue after removal. It is excellent for temporary applications at exhibitions and displays.

- 0,22mm thick
- Acrylic adhesive
- Temperature resistant up to 110⁰C
- Easy to apply and leaves no residue

Herkules 7010 can be die-cut for custom made parts and is available in all dimensions but standard widths are:

- 12mm x 50m
- 25mm x 50m
- 50mm x 50m

## CONSTRUCTION



- Acrylic adhesive
- Rayon carrier
- Acrylic adhesive
- White paper liner

## APPLICATIONS

Herkules 7010 is used in many different industries and sectors. It is very easy to apply and is ideal for temporary applications at exhibitions and displays. Typical applications are:

- Conference and exhibition halls
- Flooring
- Displays

## USER GUIDELINES

To obtain optimal adhesion the surfaces must be clean and dry. Most frequent cleaning solvent is isopropyl/water (50:50 mixture) alcohol. Use safety instructions before using cleaners. Sometimes depending on surface a primer can be used to obtain a higher bonding force. Ideal temperature for tape application is between 21°C and 38°C.

the TAPE challenge

# PRODUCT DATA

Physical Data:

| Adhesive: | Acrylic |
|---|---|
| Carrier: | Rayon |
| Thickness: | 0,22mm |
| Liner: | White siliconised paper |
| Colour: | White |
| Shelf life*: | 12 months |
| Storage: | Good storage conditions are in room temperature. Not recommended for direct exposure to sunlight or ultraviolet light. |

* From date of dispatch by ATC Tape Converting AB

Performance Data:

| Peeling strength:<br>(AFERA 4001) | 10 N/25mm |
|---|---|
| Tear resistance:<br>(DIN 53112) | 210 N/50mm |
| Heat resistance: | -30⁰C to +110⁰C |
| Condensation water resistance: | Good |
| Ageing resistance: | Very good |
| Softener resistance: | Very good |

# CONTACT INFORMATION

**ATC Adhesive Tape Converting AB**
Veddestavägen 17, Box 575
175 26 Järfälla, SWEDEN

Telephone: +46 (0)8-564 708 80      E-mail:   info@atc.se
Fax: +46 (0)8-564 708 89             Web:     www.atc.se



the TAPE challenge